

## Product group: 327 Product number: L410536

#### **Product information**

## **Specification**

#### General

Material	75% Polyolefin & 25% HT Polyester
Material type and grade	Mixed polyolefins (B5 yarn) and HT PES

## Physical properties

Colour	Blue and white	e anti-twisting colors
Construction	12 strand braided	
Density [kg/m3]	0.99	
Bongation [%]	18% at break	
Eyes 1,8mmesh bra		id protected eyes
Jacketed false		
Line Construction	12x1 braided	
Line Linear Density (LLD)	1.76 kg/m	
Line Tenacity (LT) Maximum	38.41 t/kg/m	
Line Tenacity (LT) Maximum (kNg/m)	0.38 kN/g/m	
Line Tenacity (LT) Measured	37.92 t/kg/m	
Load Bearing Linear Density (LBLD)	d Bearing Linear Density (LBLD) 1.698 kg/m	
NSBF (if requested)	Not requested	
Rotating	false	
Splice type and design	d design Tuck (6S-6Z)x	
Technical data		
Angled Break Force (ABF) % Avg NSBF D/d	= 10	181.42 (90.71)
Angled Break Force (ABF) % Avg NSBF D/d = 5		173.00 (86.50)
Angled Endurance (AE) % Avg NSBF D/d = 10		78.21
Angled Endurance (AE) % Avg NSBF D/d = 5		75.13
Average Immediate Strain (e) %LDBF:10		1.33
Average Immediate Strain (e) %LDBF:20		2.50
Average Immediate Strain (e) %LDBF:30		3.50
Average Immediate Strain (e) %LDBF:40		4.36
Average Immediate Strain (e) %LDBF:50		5.24
Axial Compression Resistance (ACR)		94.53% Avg NSBF
LDBF [kN] (from)		591
LDBF [kN] (up to)		632
LDBF [t] (from)		60.1
LDBF[t] (up to)		64.4
Line Design Break Force (LDBF)		64.4
Temperature (T) % BF at 20°C -20C		135/101
Temperature (T) % BF at 20°C 0C		124/103
Temperature (T) % BF at 20°C 20C		100/100
Temperature (T) % BF at 20°C 40C		84/93
Temperature (T) % BF at 20°C 60C		72/89
Temperature (T) % BF at 20°C 80C		57/89
Unspliced MBL [t]		71.6

# Dimensions/Weight

Diameter [mm]	57
Length [m]	300

# Performance data

DNVGL	Y
SBA	Y
Strength adjustment	10%
Var Range From	100%
Var Range To	105%

#### This page is printed from:

https://www.wilhelmsen.com/product-catalogue/products/ropes/conventional-mooring-ropes/timm-master-12-sba/timm-master-12-sba/f60-57mm-300m/