

Product group: 327

Product number: 410146

Product information

Specification

General

Material	75% Polyolefin & 25% HT Polyester
Material type and grade	Mixed polyolefins (B5 yarn) and HT PES

Physical properties

Colour	Blue and white anti-twisting colors
Construction	12 strand braided
Density	0.99
Density [kg/m3]	0.99
Elongation [%]	18% at break
Eyes	1,8mmesh braid protected eyes
Jacketed	false
Line Construction	12x1 braided
Line Linear Density (LLD)	2.096 kg/m
Line Tenacity (LT) Maximum	38.41 t/kg/m
Line Tenacity (LT) Maximum (kNg/m)	0.38 kNg/m
Line Tenacity (LT) Measured	37.87 t/kg/m
Load Bearing Linear Density (LBLD)	2.007 kg/m
Melting point	165°C
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	Tuck (6S-6Z)x4

Technical data

Angled Break Force (ABF) %Avg NSBF D/d = 10	181.42 (90.71)
Angled Break Force (ABF) %Avg NSBF D/d = 5	173.00 (86.50)
Angled Endurance (AE) %Avg NSBF D/d = 10	78.21
Angled Endurance (AE) %Avg NSBF D/d = 5	75.13
Average Immediate Strain (e) %LDBF:10	1.33
Average Immediate Strain (e) %LDBF:20	2.50
Average Immediate Strain (e) %LDBF:30	3.50
Average Immediate Strain (e) %LDBF:40	4.36
Average Immediate Strain (e) %LDBF:50	5.24
Axial Compression Resistance (ACR)	94.53% Avg NSBF
LDBF [kN] (from)	633
LDBF [kN] (up to)	746
LDBF [t] (from)	64.4
LDBF [t] (up to)	76.0
Line Design Break Force (LDBF)	76.0
Temperature (T) %BF at 20°C -20C	135/101
Temperature (T) %BF at 20°C 0C	124/103
Temperature (T) %BF at 20°C 20C	100/100
Temperature (T) %BF at 20°C 40C	84/93
Temperature (T) %BF at 20°C 60C	72/89
Temperature (T) %BF at 20°C 80C	57/89
Unspliced MBL [t]	84.5

Performance data

DNVGL	Y
SBA	Y
Strength adjustment	10%
Var Range From	100%
Var Range To	105%

This page is printed from:

<https://www.wilhelmsen.com/product-catalogue/products/ropes/conventional-mooring-ropes/timm-master-12-sba/timm-master-12-sba-f70-62mm-110m/>