

# TIMM MASTER 8 64MM 220M WHITE 2X1,8M EYE

Product group: **320**      Product number: **410095**

Timm Master 8 is one of the most selling premium mixed polymer ropes. A reliable, flexible, and tough mooring rope suitable for all ship types.

Product image

## Product information

Our most recognised product to date, long admired as a premium, mixed polymer rope solution. We have sold Timm Master to over 6,000 vessels worldwide. Our Master ropes are supplying a significant proportion of the world's largest shipping companies. This is a flexible and easily handled product made from our Timm Signal B5 polyolefin yarn and high tenacity polyester and has long been admired as a premium, mixed polymer mooring rope.

Master ropes have a low cost of ownership, very good abrasion properties and excellent UV resistance. The product is buoyant (<1% water absorption) and 18% elongation at break.

### Features

- 8-strand plaited construction
- Buoyant
- Low-torque
- UV stabilised

### Benefits

- Class leading strength-to-weight ratio
- High abrasion resistance
- Type approval from DNV GL
- Meets all OCIMF requirements
- Held in global stock inventory

## Specification

### General

<b>Invent Hazard Material (IMO/EU) classification</b>	NA
<b>Material</b>	Mixed polyolefins (B5 yarn) and HT PES
<b>Material type and grade</b>	Mixed polyolefins (B5 yarn) and HT PES

### Physical properties

<b>Colour</b>	White with 3 black marking yarns
<b>Construction</b>	8-strand plaited rope
<b>Density [kg/m<sup>3</sup>]</b>	0.99
<b>Elongation [%]</b>	18% at break
<b>Eyes</b>	1.8m protected eyes (PES)
<b>Jacketed</b>	false
<b>Line Construction</b>	8-strand braided
<b>Line Linear Density (LLD)</b>	2.137 kg/m
<b>Line Tenacity (LT) Maximum</b>	38.41 t/kg/m
<b>Line Tenacity (LT) Maximum (kN/g/m)</b>	0.38 kN/g/m
<b>Line Tenacity (LT) Measured</b>	37.85 t/kg/m
<b>Load Bearing Linear Density (LBLD)</b>	2.137 kg/m
<b>Melting point</b>	165°C
<b>NSBF (if requested)</b>	Not requested
<b>Rotating</b>	false
<b>Splice type and design</b>	Tuck (4S-4Z)x5

## Dimensions/Weight

Diameter [mm]	64
Length [m]	220

## Technical data

Angled Break Force (ABF) % Avg NSBF D/d = 10	181.42 (90.71)
Angled Break Force (ABF) % Avg NSBF D/d = 5	173.00 (86.50)
Angled Endurance (AE) % Avg NSBF D/d = 10	78.21
Angled Endurance (AE) % Avg NSBF D/d = 5	75.13
Average Immediate Strain (e) %LDBF:10	1.33
Average Immediate Strain (e) %LDBF:20	2.50
Average Immediate Strain (e) %LDBF:30	3.50
Average Immediate Strain (e) %LDBF:40	4.36
Average Immediate Strain (e) %LDBF:50	5.24
Axial Compression Resistance (ACR)	94.53% Avg NSBF
Line Design Break Force (LDBF)	80.9
Spliced MBL/LDBF [kN]	794
Temperature (T) % BF at 20°C 0C	124/103
Temperature (T) % BF at 20°C 20C	100/100
Temperature (T) % BF at 20°C -20C	135/101
Temperature (T) % BF at 20°C 40C	84/93
Temperature (T) % BF at 20°C 60C	72/89
Temperature (T) % BF at 20°C 80C	57/89
Unspliced MBL [kN]	882
Unspliced MBL [t]	89.9

## Performance data

DNVGL	Y
SBA	N
Strength adjustment	10%
Var Range From	100%
Var Range To	105%

## Approvals

Type Approved Product by DNV GL. This product is produced according to ISO 9554 and tested according to ISO 2307. Minimum Breaking Load (MBL) is according to ISO 10556 and verified by DNV GL.

Manufactured acc. to => ISO 9554, ISO 10556

Tested acc. to => ISO 2307, CI 1500A, DNVGL-CP-0100

Type Approval No => TAK0000094

## Documents

[Timm Master - Use and Care Manual](#)

[Supplier's declaration of Conformity \(SDoC\)](#)

## Related products

Is frequently bought together with

**411068** ACERA AMUNDSEN 34MM 250M PLATINUM  
2X1,8M SUPEREYE

**410167** TIMM MASTER 8 TAIL 76MM 11M WHITE 2X2,0M  
EYE

**410099** TIMM MASTER 8 68MM 220M WHITE 2X1,8M EYE

**779032** AUTODARK 300 WELDING SHIELD

**410051** TIMM MASTER 8 40MM 220M WHITE 2X1,8M EYE

**This page is printed from:**

<https://www.wilhelmsen.com/product-catalogue/products/ropes/conventional-mooring-ropes/timm-master-8/timm-master-8-64mm-220m-794kn-spliced882kn-unspliced-white-2x18m-eye/>