

Product group: 329

Product number: L410189

Product information

Specification

General

Material type and grade	Acera H16 (HMPE)
-------------------------	------------------

Dimensions/Weight

Diameter [mm]	49
Length [m]	200

Performance data

DNVGL	Y
SBA	Y
Strength adjustment	10%
Var Range From	100%
Var Range To	105%

Physical properties

Construction	12 strand braided
Density	0.97 (floating)
Elongation [%]	2-3% at break
Eyes	SuperEye
Jacketed	false
Line Construction	12x1 braided
Line Linear Density (LLD)	1.192 kg/m
Line Tenacity (LT) Maximum	162.9 tkg/m
Line Tenacity (LT) Maximum (kNg/m)	1.68 kNg/m
Line Tenacity (LT) Measured	149.1 t/kg/m
Load Bearing Linear Density (LBLD)	1.13 kg/m
Melting point	145°C- 150°C
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	Tension(12S/Z)x1

Technical data

Angled Break Force (ABF) % Avg NSBF D/d = 10	199.18 (99.59)
Angled Break Force (ABF) % Avg NSBF D/d = 5	184.68 (92.34)
Angled Endurance (AE) % Avg NSBF D/d = 10	86
Angled Endurance (AE) % Avg NSBF D/d = 5	60.04
Average Immediate Strain (e) %LDBF:10	0.2
Average Immediate Strain (e) %LDBF:20	0.42
Average Immediate Strain (e) %LDBF:30	0.62
Average Immediate Strain (e) %LDBF:40	0.82
Average Immediate Strain (e) %LDBF:50	1.01
Axial Compression Resistance (ACR)	93.16% Avg NSBF
LDBF [kN] (from)	1438
LDBF [kN] (up to)	1658
LDBF [t] (from)	146.6
LDBF [t] (up to)	169.1
Line Design Break Force (LDBF)	169.1
Temperature (T) % BF at 20°C -20C	111
Temperature (T) % BF at 20°C 0C	110
Temperature (T) % BF at 20°C 20C	100
Temperature (T) % BF at 20°C 40C	94
Temperature (T) % BF at 20°C 60C	86
Temperature (T) % BF at 20°C 80C	57
Unspliced MBL [t]	186