

Last updated: 04/07/2024 06:26:47

# ACERA AMUNDSEN SBA S125 [42MM] 200M

Product group: **329**    Product number: **410040**



## Product information

## Specification

General

Material type and grade	Acera H16 (HMPE)
-------------------------	------------------

Physical properties

Density	0.97 (floating)
Jacketed	false
Line Construction	12x1 braided
Line Linear Density (LLD)	0.914 kg/m
Line Tenacity (LT) Maximum	162.9 t/kg/m
Line Tenacity (LT) Maximum (kN/g/m)	1.60 kN/g/m
Line Tenacity (LT) Measured	151.2 t/kg/m
Load Bearing Linear Density (LBLD)	0.86 kg/m
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	Tension (12S/Z)x1
X - Line Linear Density (LLD)	0.914 kg/m
X - Line Tenacity (LT) Maximum	162.9 t/kg/m
X - Line Tenacity (LT) Maximum (kN/g/m)	1.60 kN/g/m
X - Line Tenacity (LT) Measured	151.2 t/kg/m
X - Load Bearing Linear Density (LBLD)	0.86 kg/m
X - Splice type and design	Tension (12S/Z)x1

Dimensions/Weight

Diameter [mm]	42
Length	200
Length [m]	200

Technical data

Angled Break Force (ABF) % Avg NSBF D/d = 10	199.18 (99.59)
Angled Break Force (ABF) % Avg NSBF D/d = 5	184.68 (92.34)
Angled Endurance (AE) % Avg NSBF D/d = 10	86
Angled Endurance (AE) % Avg NSBF D/d = 5	60.04
Average Immediate Strain (e) %LDBF:10	0.20
Average Immediate Strain (e) %LDBF:20	0.42
Average Immediate Strain (e) %LDBF:30	0.62
Average Immediate Strain (e) %LDBF:40	0.82
Average Immediate Strain (e) %LDBF:50	1.01
Axial Compression Resistance (ACR)	93.16% Avg NSBF
LDBF [kN] (from)	1059
LDBF [kN] (up to)	1274
LDBF [t] (from)	107.9
LDBF [t] (up to)	129.9
Line Design Break Force (LDBF)	129.9
Temperature (T) % BF at 20°C -20C	111
Temperature (T) % BF at 20°C 0C	110
Temperature (T) % BF at 20°C 20C	100
Temperature (T) % BF at 20°C 40C	94
Temperature (T) % BF at 20°C 60C	86
Temperature (T) % BF at 20°C 80C	57
Unspliced MBL [t]	143
X - Angled Break Force (ABF) % Avg NSBF D/d = 10	199.18 (99.59)
X - Angled Break Force (ABF) % Avg NSBF D/d = 5	184.68 (92.34)
X - Angled Endurance (AE) % Avg NSBF D/d = 10	86
X - Angled Endurance (AE) % Avg NSBF D/d = 5	60.04
X - Average Immediate Strain (e) %LDBF:10	0.20
X - Average Immediate Strain (e) %LDBF:20	0.42
X - Average Immediate Strain (e) %LDBF:30	0.62
X - Average Immediate Strain (e) %LDBF:40	0.82
X - Average Immediate Strain (e) %LDBF:50	1.01
X - Axial Compression Resistance (ACR)	93.16% Avg NSBF

<b>X - Axial Compression Resistance (ACR)</b>	93.16% Avg NSBF
<b>X - LDBF [kN] (from)</b>	1059
<b>X - LDBF [kN] (up to)</b>	1274
<b>X - LDBF [t] (from)</b>	107.9
<b>X - LDBF [t] (up to)</b>	129.9
<b>X - Line Design Break Force (LDBF)</b>	129.9
<b>X - Temperature (T) %BF at 20°C -20C</b>	111
<b>X - Temperature (T) %BF at 20°C 0C</b>	110
<b>X - Temperature (T) %BF at 20°C 20C</b>	100
<b>X - Temperature (T) %BF at 20°C 40C</b>	94
<b>X - Temperature (T) %BF at 20°C 60C</b>	86
<b>X - Temperature (T) %BF at 20°C 80C</b>	57
<b>X - Unspliced MBL [t]</b>	143

#### Performance data

<b>DNVGL</b>	Y
<b>SBA</b>	Y
<b>Strength adjustment</b>	10%
<b>Var Range From</b>	100%
<b>Var Range To</b>	105%

## Documents

### media

[Wilhelmsen Use and Care Acera Amundsen](#)

This page is printed from

<https://www.wilhelmsen.com/product-catalogue/products/ropes/high-performance-mooring-rope/acera-amundsen-sba/acera-amundsen-sba-s125-42mm-200m2/>