

---

# ACERA AMUNDSEN SBA S145 [45MM] 200M

Product group: **329**    Product number: **L412989**

Product image

## Product information

## Specification

### General

|                         |                  |
|-------------------------|------------------|
| Material type and grade | Acera H16 (HMPE) |
|-------------------------|------------------|

### Dimensions/Weight

|               |     |
|---------------|-----|
| Diameter [mm] | 45  |
| Length [m]    | 200 |

### Performance data

|                     |      |
|---------------------|------|
| DNVGL               | Y    |
| SBA                 | Y    |
| Strength adjustment | 10%  |
| Var Range From      | 100% |
| Var Range To        | 105% |

### Physical properties

|                                     |                   |
|-------------------------------------|-------------------|
| Construction                        | 12 strand plaited |
| Density [kg/m3]                     | 0.97 (floating)   |
| Elongation [%]                      | 2-3% at break     |
| Eyes                                | Supereye          |
| Jacketed                            | false             |
| Line Construction                   | 12x1 braided      |
| Line Linear Density (LLD)           | 1.03 kg/m         |
| Line Tenacity (LT) Maximum          | 162.9 t/kg/m      |
| Line Tenacity (LT) Maximum (kN/g/m) | 1.68 kN/g/m       |
| Line Tenacity (LT) Measured         | 150.2 t/kg/m      |
| Load Bearing Linear Density (LBLD)  | 1.013 kg/m        |
| NSBF (if requested)                 | Not requested     |
| Rotating                            | false             |
| Splice type and design              | Tension (12S/Z)x1 |

### Technical data

|  |                 |
|--|-----------------|
| Angled Break Force (ABF) % Avg NSBF D/d = 10 | 199.18 (99.59)  |
| Angled Break Force (ABF) % Avg NSBF D/d = 5  | 184.68 (92.34)  |
| Angled Endurance (AE) % Avg NSBF D/d = 10    | 86.00           |
| Angled Endurance (AE) % Avg NSBF D/d = 5     | 60.04           |
| Average Immediate Strain (e) %LDBF:10        | 0.20            |
| Average Immediate Strain (e) %LDBF:20        | 0.42            |
| Average Immediate Strain (e) %LDBF:30        | 0.62            |
| Average Immediate Strain (e) %LDBF:40        | 0.82            |
| Average Immediate Strain (e) %LDBF:50        | 1.01            |
| Axial Compression Resistance (ACR)           | 93.16% Avg NSBF |
| LDBF [kN] (from)                             | 1275            |
| LDBF [kN] (up to)                            | 1437            |
| LDBF [t] (from)                              | 130             |
| LDBF [t] (up to)                             | 146.5           |
| Line Design Break Force (LDBF)               | 146.5           |
| Temperature (T) % BF at 20°C 0C              | 110             |
| Temperature (T) % BF at 20°C 20C             | 100             |
| Temperature (T) % BF at 20°C -20C            | 111             |
| Temperature (T) % BF at 20°C 40C             | 94              |
| Temperature (T) % BF at 20°C 60C             | 86              |
| Temperature (T) % BF at 20°C 80C             | 57              |
| Unspliced MBL [t]                            | 161.6           |

**This page is printed from:**

<https://www.wilhelmsen.com/product-catalogue/products/ropes/high-performance-mooring-rope/acera-amundsen-sba/acera-amundsen-sba-s145-45mm-200m/>