

Last updated: 04/07/2024 06:26:46

ACERA AMUNDSEN SBA S145 [45MM] 220M BLUE

Product group: **329** Product number: **L410190**



Product information

Specification

General

Material type and grade	Acera H16 (HMPE)
--------------------------------	------------------

Dimensions/Weight

Diameter [mm]	45
Length	220
Length [m]	220

Physical properties

Construction	12 strand plaited
Density	0.97 (floating)
Elongation [%]	2-3% at break
Eyes	Supereye
Jacketed	false
Line Construction	12x1 braided
Line Linear Density (LLD)	1.03 kg/m
Line Tenacity (LT) Maximum	162.9 t/kg/m
Line Tenacity (LT) Maximum (kN/g/m)	1.60 kN/g/m
Line Tenacity (LT) Measured	150.2 t/kg/m
Load Bearing Linear Density (LBLD)	0.98 kg/m
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	Tension(12S/Z)x1
X - Line Linear Density (LLD)	1.03 kg/m
X - Line Tenacity (LT) Maximum	162.9 t/kg/m
X - Line Tenacity (LT) Maximum (kN/g/m)	1.60 kN/g/m
X - Line Tenacity (LT) Measured	150.2 t/kg/m
X - Load Bearing Linear Density (LBLD)	0.98 kg/m
X - Splice type and design	Tension(12S/Z)x1

Technical data

Angled Break Force (ABF) %Avg NSBF D/d = 10	199.18 (99.59)
Angled Break Force (ABF) %Avg NSBF D/d = 5	184.68 (92.34)
Angled Endurance (AE) %Avg NSBF D/d = 10	86.00
Angled Endurance (AE) %Avg NSBF D/d = 5	60.04
Average Immediate Strain (e) %LDBF:10	0.20
Average Immediate Strain (e) %LDBF:20	0.42
Average Immediate Strain (e) %LDBF:30	0.62
Average Immediate Strain (e) %LDBF:40	0.82
Average Immediate Strain (e) %LDBF:50	1.01
Axial Compression Resistance (ACR)	93.16% Avg NSBF
LDBF [kN] (from)	1275
LDBF [kN] (up to)	1437
LDBF [t] (from)	130
LDBF [t] (up to)	146.5
Line Design Break Force (LDBF)	146.5
Temperature (T) %BF at 20°C -20C	111
Temperature (T) %BF at 20°C 0C	110
Temperature (T) %BF at 20°C 20C	100
Temperature (T) %BF at 20°C 40C	94
Temperature (T) %BF at 20°C 60C	86
Temperature (T) %BF at 20°C 80C	57
Unspliced MBL [t]	161.6
X - Angled Break Force (ABF) %Avg NSBF D/d = 10	199.18 (99.59)
X - Angled Break Force (ABF) %Avg NSBF D/d = 5	184.68 (92.34)
X - Angled Endurance (AE) %Avg NSBF D/d = 10	86.00
X - Angled Endurance (AE) %Avg NSBF D/d = 5	60.04
X - Average Immediate Strain (e) %LDBF:10	0.20
X - Average Immediate Strain (e) %LDBF:20	0.42
X - Average Immediate Strain (e) %LDBF:30	0.62
X - Average Immediate Strain (e) %LDBF:40	0.82

X - Average Immediate Strain (e) %LDBF:50	1.01
X - Axial Compression Resistance (ACR)	93.16% Avg NSBF
X - LDBF [kN] (from)	1275
X - LDBF [kN] (up to)	1437
X - LDBF [t] (from)	130
X - LDBF [t] (up to)	146.5
X - Line Design Break Force (LDBF)	146.5
X - Temperature (T) %BF at 20°C -20C	111
X - Temperature (T) %BF at 20°C 0C	110
X - Temperature (T) %BF at 20°C 20C	100
X - Temperature (T) %BF at 20°C 40C	94
X - Temperature (T) %BF at 20°C 60C	86
X - Temperature (T) %BF at 20°C 80C	57
X - Unspliced MBL [t]	161.6

Performance data

DNVGL	Y
SBA	Y
Strength adjustment	10%
Var Range From	100%
Var Range To	105%

This page is printed from

<https://www.wilhelmsen.com/product-catalogue/products/ropes/high-performance-mooring-rope/acera-amundsen-sba/acera-amundsen-sba-s145-45mm-220m-blue/>