

Product group: **329** Product number: **L413352**

Product information

Specification

General

Dimensions/Weight

Diameter [mm]	25
Length	180

Physical properties

Jacketed	false
Line Construction	12x1 braided
Line Linear Density (LLD)	0.345 kg/m
Line Tenacity (LT) Maximum	162.9 t/kg/m
Line Tenacity (LT) Maximum (kN/g/m)	1.68 kN/g/m
Line Tenacity (LT) Measured	159.5 t/kg/m
Load Bearing Linear Density (LBLD)	0.323 kg/m
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	Tension (12S/Z)x1

Technical data

Angled Break Force (ABF) % Avg NSBF D/d = 10	199.18 (99.59)
Angled Break Force (ABF) % Avg NSBF D/d = 5	184.68 (92.34)
Angled Endurance (AE) % Avg NSBF D/d = 10	86
Angled Endurance (AE) % Avg NSBF D/d = 5	60.04
Average Immediate Strain (e) %LDBF:10	0.2
Average Immediate Strain (e) %LDBF:20	0.42
Average Immediate Strain (e) %LDBF:30	0.62
Average Immediate Strain (e) %LDBF:40	0.82
Average Immediate Strain (e) %LDBF:50	1.01
Axial Compression Resistance (ACR)	93.16% Avg NSBF
LDBF [kN] (from)	406
LDBF [kN] (up to)	505
LDBF [t] (from)	42
LDBF [t] (up to)	51.5
Line Design Break Force (LDBF)	51.5
Temperature (T) % BF at 20°C -20C	111
Temperature (T) % BF at 20°C 0C	110
Temperature (T) % BF at 20°C 20C	100
Temperature (T) % BF at 20°C 40C	94
Temperature (T) % BF at 20°C 60C	86
Temperature (T) % BF at 20°C 80C	57
Unspliced MBL [t]	57.2

Performance data

DNVGL	Υ
SBA	Y
Strength adjustment	10%
Var Range From	100%
Var Range To	105%

This page is printed from:

https://www.wilhelmsen.com/product-catalogue/products/ropes/high-performance-mooring-rope/acera-amundsen-sba/acera-amundsen-sba-s50-25mm-180m/sen-sba/acera-amundsen-sba-s50-25mm-180m/sen-sba/acera-amundsen-sba-s50-25mm-180m/sen-sba/acera-amundsen-sba-s50-25mm-180m/sen-sba/acera-amundsen-sba-s50-25mm-180m/sen-sba/acera-amundsen-sba-s50-25mm-180m/sen-sba/acera-amundsen-sba-s50-25mm-180m/sen-sba/acera-amundsen-sba-s50-25mm-180m/sen-sba/acera-amundsen-sba-s50-25mm-180m/sen-sba-s50-