

Product group: 325 Product number: 410159

Timm Master 8 Tail is an 8-strand floating mooring tail which effectively absorb shock and energy in mooring systems.

Product information

Our best selling mooring tail made from the Timm Master rope design, sold to over 6 000 vessels. Made of HT polyester and B5 polyolefin yarns which effectively absorb shock/energy in mooring systems. Typically used with steel wire and HMPE ropes. Compared to nylon stretchers, this product remains elastic for a longer period. It performs better in wet conditions, providing equal breaking strength under wet and dry conditions.



Features

- Protected eyes
- Buoyant
- High elongation

Benefits

- 15-20% lighter than PES and nylon tails
- Excellent abrasion and UV resistance
- Smooth and gripable surface
- Meets all OCIMF requirements

Specification

General

Invent Hazard Material (IMO/EU) classification	NA
Material type and grade	Mixed polyolefins (B5 yarn) and HT PES

Dimensions/Weight

Diameter [mm]	72
Length [m]	11

Performance data

DNVGL	Y
SBA	N
Strength adjustment	10%
Var Range From	125%
Var Range To	130%

Approvals

Type Approved Product by DNV GL.
This product is produced according to ISO 9554 and tested according to ISO 2307. Minimum Breaking Load (MBL) is according to ISO 10556 and verified by DNV GL.

Manufactured acc. to => ISO 9554, ISO 10556
Tested acc. to => ISO 2307, CI 1500A, DNVGL-CP-0100
Type Approval No => TAK0000094

Documents

[Timm Master Tail - Use and Care Manual](#)

[SDoC and MD for IHM](#)

Related products

Is frequently bought together with

410079
TIMM MASTER 8 56MM 220M WHITE 2X1,8M EYE

Physical properties

Colour	White with 3 black marking yarns
Construction	8-strand plaited
Density [kg/m3]	0.99
Jacketed	false
Line Construction	8-strand braided
Line Linear Density (LLD)	2.699 kg/m
Line Tenacity (LT) Maximum	38.41 t/kg/m
Line Tenacity (LT) Maximum (kN/g/m)	0.38 kN/g/m
Line Tenacity (LT) Measured	37.77 t/kg/m
Load Bearing Linear Density (LBLD)	2.699 kg/m
Melting point	165°C
NSBF (if requested)	Not requested
Rotating	false
Splice type and design	Tuck (4S-4Z)x5

Technical data

Average Immediate Strain (e) %LDBF:10	1.33
Average Immediate Strain (e) %LDBF:20	2.50
Average Immediate Strain (e) %LDBF:30	3.50
Average Immediate Strain (e) %LDBF:40	4.36
Average Immediate Strain (e) %LDBF:50	5.24
Dynamic stiffness (Kex) Exposed	20.65xTDBF
Dynamic stiffness (Ksh) Sheltered	16.14xTDBF
Line Design Break Force (LDBF)	102.0
Spliced MBL DRY [t]	102.0
Spliced MBL/LDBF [kN]	1001
Tension-tension endurance CTF 20%	1.99342E+13
Tension-tension endurance CTF 50%	205233732
Unspliced MBL [t]	113.3

This page is printed from:

<https://www.wilhelmsen.com/product-catalogue/products/ropes/rope-stretchers/timm-master-8-tail/timm-master-8-tail-72mm-11m-1001kn-spliced-white-2x20m-eye/>