

Product group: **090** Product number: **777972** 

Solid wire for gas metal arc welding of copper-aluminium alloys, e.g., Yorcalbro pipes.

#### **Product information**

This product supersedes product no: 590091

Unitor IALBRO-W is suited for welding most bronze/brass alloys, including aluminum bronzes like Yorcalbro, in wrought as well as cast forms.

#### **Features**

- High mechanical strength and toughness
- It is also suited for rebuilding or joining materials to steel or cast iron, and for wear or corrosion resistant overlays on steel and cast iron.

#### Renefits

- Less possibility for joint failure during operation
- The weld deposit have high resistance to corrosion and wear

## **Specification**

## General Dimensions/Weight

Invent Hazard Material (IMO/EU) classification	NA	Diameter [mm]	0.8
		Weight [kg]	5

#### Technical data

AWS	A5.7: ERQu Al-A1
Polarity	DC+
Voltage [V]	22 main supply
Wire Speed (m/min)	7.5

## **Documents**

SDoC and MD for IHM

# Directions for use

Use pure Argon as shielding gas

Ensure good surface preparation i.e., use only stainless steel abrasive discs or brush for grinding or cleaning

Yorcalbro pipes with a small diameter and thin walls should be TIG welded. If there is an overlap joint (capillary joint) Silver brazing should be considered

## **Related products**

## Is frequently bought together with

## 699421

23/14-322N 2.5X300MM84 PCS 1.7 KG

# 699439

23/14-322N 3.2X350MM50 PCS 2.0 KG

## 597518

S316M-GF,221,0.9MMWELD. WIRE 2.5KG

## 590117

GPS-W 200 0,8MM WELD. WIRE 5,0KG

## This page is printed from:

https://www.wilhelmsen.com/product-catalogue/products/welding/arc-welding-consumables-and-storing/arc-welding-wires/ialbro-w-237-08 mm-weld.-wire-50 kg

