

Product group: **090** Product number: **597518**

Stainless steel flux cored welding wire for gas metal arc welding of stainless steel grades SS308L and SS316L.



Product information

Unitor S 316 M-GF is a rutile flux cored wire designed for welding 19% Cr, 12% Ni, 3% Mo types of stainless steel.

Features

- High mechanical strength and toughness
- High content of molybdenum
- It is also suitable for related stabilised steel grades if service temperature is below 400°C

Benefits

- Application include welding on base materials AISI-304 and AISI -316
- High productivity welding as the wire operates with a very stable, spatter free arc producing a bright, smooth weld bead surface and the slag is self-releasing.

Specification

General

Invent Hazard Material (IMO/EU) classification	NA
--	----

Dimensions/Weight

Diameter [mm]	0.9
Weight [kg]	2.5

Technical data

AWS	A5.22:E316LT1-4/-1
Polarity	DC+
Voltage [V]	
Wire Speed (m/min)	11

Documents

[SDoC and MD for IHM](#)

Directions for use

Use preferably 80% Ar/20% CO₂ (UNIMIX) as shielding gas
 Pure CO₂ can also be used but for positional welding, Ar/CO₂ is highly recommended for good welding results

Related products

Is frequently bought together with

- 233601**
AG 60 252 2.0 X 500MM 0,5KG
- 160100**
MS-W-201 SELFSHIELDWIRE 0,8MM 4.5KG
- 602979**
18/8MO-221 2.0 X 500 MM 0,5KG
- 590117**
GPS-W200 0,8MM WELD. WIRE 5,0KG

This page is printed from:

<https://www.wilhelmsen.com/product-catalogue/products/welding/arc-welding-consumables-and-storing/arc-welding-wires/s316m-gf2210.9mm-weld.-wire-2.5kg>