



18/8-321N 3.2X300MM 54 PCS 1.7 KG

Product group: **095** Product number: **699413**

Electrode for welding of stainless steel.



Product information

This product supersedes product no: **606435**

Rutile-basic electrodes for welding corrosion-resistant austenitic steels containing 16-18% Chromium, 10-14% Nickel and 2-3% Molybdenum, e.g. AISI:316/316L, TP-316/H, CF-3M/8M/8C, CPF 8M/10 MC. LMA electrode

Features

- LMA electrode
- Unitor high density polyethylene packing
- Approved by classification societies for welding of stainless steel

Benefits

- Electrodes can be exposed longer in the open
- Can be stored for long time without moisture pick up
- In compliance with maritime rules and regulations

Specification

General

Invent Hazard Material (IMO/EU) classification	NA
--	----

Dimensions/Weight

Diameter [mm]	3.2
Weight [kg]	1.7

Technical data

AWS	E 316L-17
Polarity	AC,DC +

Performance data

Amperage [A]	135
--------------	-----

Rutile-basic electrodes for welding corrosion-resistant austenitic steels containing 16-18% Chromium, 10-14% Nickel and 2-3% Molybdenum, e.g. AISI:316/316L, TP-316/H, CF-3M/8M/8C, CPF 8M/10 MC. LMA electrode

Related products

Is consumable by

669999 ELECTRODE CABINET COMPACT EMPTY

Is frequently bought together with

699165 GPO-302N 2.5X350MM 295 PCS 5,2KG

699272 LH-314N 3.2X450MM96 PCS 5KG

699173 GPO-302N 3.2X350MM 190 PCS 5.4 KG

699405 18/8-321N 2.5X300MM 89 PCS 1.7 KG

699264 LH-314N 2.5X350MM 161 PCS 4.0 KG

This page is printed from:

<https://www.wilhelmsen.com/product-catalogue/products/welding/arc-welding-consumables-and-storing/coated-stick-electrodes/188-32In-3.2x300mm-54-pcs-1.7-kg/>