

Product group: **096**    Product number: **699496**

Electrode for welding of cast iron with pure nickel.



## Product information

This product supersedes product no: **602946**

Nickel electrodes (95% Ni) for welding of gray cast iron to itself or to steel. Especially good for old oil-soaked and corroded cast iron, and also for joining cast iron to steel, copper, copper alloys and stainless steel.

The two types of UNITOR cast iron welding electrode i.e., Nickel-333N (Pure Nickel) and NiFe-334N (Nickel Iron) whereby the pure nickel grade will produce a softer, more malleable weld deposit or lower strength and ductility than those of nickel iron.

Hence, Nickel-333N should be used where maximum machinability of weld deposit is required or where low concentration of weld stresses e.g., these include applications for thin plates, machinery parts, frames and housings.

### Features

- Unitor high density polyethylene packing
- Superb arc stability
- Easy slag removal and smooth weld surface
- Very good on oily cast iron

### Benefits

- Long storage lifespan without moisture pick up
- Easy to use
- Little surface treatment needed
- Less porosity in deposit resulting in less required grinding

## Specification

### General

Invent Hazard Material (IMO/EU) classification	NA
--	----

### Dimensions/Weight

Diameter [mm]	2.5
Weight [kg]	2

### Technical data

AWS	A5.15: EN-C1
Polarity	AC,DC+/-

### Performance data

Amperage [A]	110
--------------	-----

## Documents

[SDoC and MD for IHM](#)

## Related products

### Is frequently bought together with

**699405**  
18/8-321N 2.5X300MM89 PCS 1.7 KG

**699173**  
GPO-302N 3.2X350MM 190 PCS 5.4 KG

**699264**  
LH-314N 2.5X350MM 161 PCS 4.0 KG

**699272**  
LH-314N 3.2X450MMØ6 PCS 5KG

**699165**  
GPO-302N 2.5X350MM 295 PCS 5,2KG

### This page is printed from:

<https://www.wilhelmsen.com/product-catalogue/products/welding/arc-welding-consumables-and-storing/coated-stick-electrodes/nickel-333n-2.5x300mm-121pcs-2.0-kg>