

Product group: 093 Product number: 519744

Bare silver brazing rod for most metals and able to use on larger joint gap up to 1.0mm.

Product information

Silver solder (44% silver) for capillary brazing of all types of steel, copper alloys, nickel alloys, cast steel etc. Does not contain cadmium. Should not be used on seawater piping like cunifer or yorcalbro, where a silver content of minimum 50% is needed. Use with AG-45/60 Brazing Flux BAF.

Features

- •
- Unique chemistry give high strength Cadmium and Phosphorus free, suitable for marine use Low melting point
- •

Benefits

- · Less possibility for joint to fail during operation
- Safe to use
- Job is done faster •

Specification

General

Invent Hazard Material (IMO/EU) classification

Documents

SDoC and MD for IHM

Directions for use

The label on each container fully identifies the contents, and also gives basic information on application areas. Complete information on each rod, and instructions for use are given in the handbook for Maritime Welders.

NA

Flame setting: Use neutral flame

Related products

Is part of bundle 589861

GASWELDING CABINET COMPLETE

Is frequently bought together with 699264 LH-314N 2.5X350MM 161 PCS 4.0 KG 699165 GPO-302N 2.5X350MM 295 PCS 5,2KG 233601 AG 60 252 2.0 X 500MM 0,5KG 233604 AG 45/60 BRAZING FLUX BAF.250G

This page is printed from:

https://www.wilhelmsen.com/product-catalogue/products/welding/gas-welding-brazing-cutting/gas-welding-and-brazing-consumables/ag-45-253-2.0-x-500nm-04kg

